



Product Information

Polycarbonate Maxi-Blast PC

Short description	PC	
Designation	Polycarbonate	
Shape	Cylindrical	
Application	Deburring of thermoset parts and light metal parts	
Blasting Systems	air blast- and centrifugal wheel systems	
Indication / chemical composition	Polycarbonate	
Hardness (New Grain)	HRM 70 - 74 ≈ HRR 120	
Hardness (Operating Mix)	identical to new Grain	
Specific Density [kg/l]	1,2	
Bulk Density [kg/l]	approx. 0,7	
Specific Characteristics	colours: white, red, blue to facilitate the use, if you are working on a number of different materials, for you can keep them apart easier Anti static agent within the Polymer structure / Melting Point > 150°C	
Storage	several years, considering dry storage	
Particle Size	US-Mesh (10 / 10) = 2,03 x 2,03 mm	US-Mesh (20 / 20) = 0,76 x 0,76 mm
	US-Mesh (12 / 12) = 1,52 x 1,52 mm	0,50 x 0,50 mm
	US-Mesh (16 / 16) = 1,14 x 1,14 mm	0,38 x 0,38 mm